


### PRODUCT DESCRIPTION & USE

**Fleetwood Stay White Undercoat** is a 100% acrylic emulsion based primer sealer especially formulated for the professional painter. This product provides a combination of excellent coverage and adhesion with easy application. Designed for interior wood and plaster surfaces this product allows same day priming and finishing with either water based or white spirit based finishes. low odour. With added advantages of being water based, quick drying and low odour.

### KEY BENEFITS

- Excellent adhesion and durability
- Low odour
- Great coverage

### AVAILABLE IN SIZES



### COLOUR RANGE

#### Fleetwood Stay White Undercoat

Available only in brilliant white but may be tinted using the Fleetwood Colour Answers tinting system

### VOC CONTENT

Contains max VOC; 10g/l  
Conforms to EU 2010 Directive (Cat A/d) 130g/l

### COMPOSITION (NOMINAL)

**Pigment:** Lightfast Pigments.  
**Binder:** Acrylic Emulsion.  
**Solvent:** Water.

### SOLIDS - SPECIFIC GRAVITY

**Volume Solids** 34.0 % (+/- 2%)  
**Weight Solids** 51.0 % (+/- 2%)  
**Specific Gravity** 1.30 g/l (+/- 0.15)

### SURFACE PREPARATION

Surfaces to be painted must be in sound condition. Use in accordance with good painting practice. Remove oil, grease and flaking material. Rub down previously painted surfaces with fine abrasive paper and rinse thoroughly. Avoid dust inhalation

### APPLICATION



Brush, roller, spray & airless spray. For best brushing results use a synthetic brush such as Fleetwoods Pro-D. As with other water-based paints, do not apply in temperatures below 5°C

### SPREADING RATE



As a guide a coverage rate of up to 16m<sup>2</sup>/litre can be achieved under normal conditions. Coverage will be dependent on the porosity and evenness of the substrate.

### REDUCTION

Reduce by up to 10% as required by application and or equipment.

### SPRAY RECOMMENDATIONS

**Conventional Spray:** Satisfactory through most equipment.  
**Airless Spray:** A typical recommendation for airless spray application is a minimum working pressure on paint of 140 kg/cm<sup>2</sup> (2000 lb/in<sup>2</sup>) with a spray tip size of 0.38mm to 0.46mm (15 - 18thou) spray tip angle 65°. Filter mesh 60

### DRYING TIMES (SINGLE COAT, STANDARD THICKNESS)



**Touch Dry:** 30 minutes  
**Recoat:** 4 hours

This is dependent upon temperature and humidity. Darker colours may take longer

### TINTING INSTRUCTIONS

Tint only with Fleetwood tinting systems

### CLEANING UP



Clean up with soap and water. After cleaning up be sure to flush spray equipment with solvent to prevent rusting following manufacturer's instructions. Dispose of can in accordance with local authority guidelines.

### PRECAUTIONS

Keep out of reach of children. Ensure good ventilation during application and drying. If the product comes in contact with the eyes rinse immediately with plenty of water. To remove splashes from skin use soap and water or a recognised skin cleaner. Do not take internally. **Contains no added lead.**

### PREVIOUSLY PAINTED SURFACES

If in sound condition, clean the surface of all foreign material. Glossy surfaces must be rubbed down to provide a key. Stir well before use. If paint is peeling clean to sound substrate and treat as new.

### FOLLOW US ON

Online: [www.fleetwood.ie](http://www.fleetwood.ie)  
Email: [info@fleetwood.ie](mailto:info@fleetwood.ie)  
Phone: 049 8547209

